

sunbelt A50, sunbelt A50 HT

EN-Standard

Basisglas	Ebene	Glasstärke [mm]	sichtbarer Lichtbereich			solare Strahlung			g-Wert [%]	b-Wert (g-Wert/0,8) [%]	shading coefficient (g-Wert/0,87) [%]	Farbwiedergabeindex R_a	U_g -Wert [W/m ² K] (90% Argon)
			Transmission [%]	Reflexion [%]		Transmission [%]	Reflexion [%]	Absorption [%]					
				außen	innen								
substrate	coated glass surface	standard thickness [mm]	visible light			total solar energy			solar factor (SF) [%]	b-value (SF/0.8) [%]	shading coefficient (SF/0.87) [%]	colour rendering index	U_g -value [W/m ² K] (90% argon)
transmittance [%]	reflectance [%]		transmittance [%]	reflectance [%]	absorbance [%]								
	outside	inside				outside							
Floatglas clear	#2	6 16 4	53	18	12	26	30	45	28	35	32	94	1,0

Glasfarben abweichend von Farben in diesem Prospekt.

Alle technischen Werte nach EN 410 und EN 673 ($\Delta T = 15$ K), Produktionstoleranzen nach EN 1096.

Alle Produkte sind ausschließlich für den Einsatz auf Ebene #2 freigegeben.

Werte können sich im Zuge der Produktweiterentwicklung ändern. Irrtümer und Fehler nicht ausgeschlossen.

Stand: Januar 2017

Glass colours shown are for reference only and do not represent actual glass colour.

Performance data are calculated using EN 410 and EN 673 ($\Delta T = 15$ K), manufacturing tolerances EN 1096.

All products are approved only for use on surface #2.

arcon reserves the right to change product performance characteristics without notice and without obligation.

rev: January 2017

